



High Performance Optimised Hot Melt Adhesive



Product Description

Heatspek MAX 7000 is a premium high performance hot melt packaging adhesive formulated with a unique blend of metallocene polymers, optimised with a unique tackifier blend for superior line performance. This high performance adhesive is engineered to delivered excellent adhesion onto a wide range of cardboard and card types including non-porous and functional surfaces. Specifically formulated for reliable performance for production facilities with a wide range of production variables or requiring high heat resistance properties.

Product Advantages

- Heatspek MAX 7000 will perform on a wide variety of substrate types and line speeds.
- Heatspek MAX 7000 has clean running, anti-charring properties reducing oxidisation.
- Heatspek MAX 7000 has superior rheological properties improving initial tack and set speed.
- Heatspek MAX 7000 possesses green bond and hot tack reducing reliable on mechanical set up.
- Heatspek MAX 7000 will provide extremem thermal heat resistance.

Application

Heatspek MAX 5000 should be applied between 150°C and 175°C through a nozzle system.

i Technical Information

Adhesive type	Olefin Metallocene Resins	Viscosity	175°C - 1090cps
Ring and ball softening point	112°C	Adhesive open time	Long
Adhesive set time	Fast	Adhesive molten tack	High
Colour	White	Shape	Granule

✓ Health & Safety

All the constituent parts of this adhesive comply with American FDA under CFR 21.175.105.

Health and Safety: Users must first read the Safety Data Sheet. Users should familiarize themselves with all the safety aspects of the product prior to usage.

⚠ Product Disclaimer

"Since the use and application of this product is beyond our control we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty. In every case we recommend that the customer conducts their own testing and accordingly determines, to their satisfaction, its suitability for their purpose under the operating conditions in which they will use the product/s.

For additional information, phone our Customer Service Centre on 1300 729 863.

October 2018 - This Data Sheet supersedes those previously issued.